



## Product Specification

Product:	<b>Fast-Dry Silver Paste</b>
Part Number:	<b>01L-2908A</b>

- ※ Rapid curing at room temperature (conductive without heating)
- ※ Compatible with flexible substrates, ceramics, glass, metals, etc.
- ※ Easy to use
- ※ Applicable by dispensing, brushing, or spraying after dilution
- ※ High silver content with low resistance
- ※ Excellent adhesion

### Application Scope :

A series of single-component conductive pastes, one of which is a fast-drying conductive silver paste for circuit repair. This paste has a wide range of application substrates (such as PET, glass, ceramics, and other soft or hard substrates), demonstrating excellent compatibility with these materials. Electrodes fabricated using this paste exhibit a bright, fine appearance and dense structure after curing.

### Usage Conditions :

Substrate	Substrates such as PET, PI, glass, ceramics, and metals
Usage Method	Spotting, Scraping
Solidify	After construction, it can dry naturally when exposed to air. (Generally, surface drying takes 10-30 minutes, and complete drying occurs within 2 hours. The longer the exposure time, the lower the resistance of the connection will be.) If conditions permit, baking at temperatures below 150°C is recommended; alternatively, accelerated curing can be achieved through enhanced ventilation. The specific baking temperature and time can be adjusted according to actual needs, generally ranging from 5 to 20 minutes.
Thinner	ST-1001

**Characteristics :****Paste Characteristics :**

Characteristic		Standard	Test Method And Conditions
1	Fineness	$\leq 5\mu\text{m}$	FOG test
2	Viscosity	120-320Pa.s	Brookfield HBT (Boli Fei) viscometer, rotor SC4-14/6R, 10 rpm, with adjustable viscosity at $25\pm 1^\circ\text{C}$ according to user requirements.

**Save Conditions And Validity Period :**

The product shall be stored in a sealed container at an ambient temperature of  $5\text{-}15^\circ\text{C}$ , with a shelf life of 3 months from the date of manufacture.

**Packaging Method :**

Standard packaging, 20g/10ml syringe vial, other capacities available for repackaging as required.

**Matters Need Attention :**

- a. After removal from the refrigerator, the product should be left at room temperature until temperature equilibrium is achieved before opening and use. (It is generally recommended to remove and place at room temperature 4 hours prior to use).
- b. This slurry contains organic solvents and should be used in well-ventilated areas. Avoid contact with eyes, skin, or clothing during use, and keep away from sources of ignition or burning materials.  
If contact occurs, clean with a cleaning solution.