



Product Specification

Product:	Conductive Silver Paste
Part Number:	01H-3605

Application Scope :

This product is suitable for use as electrodes in piezoelectric ceramics and transducer products.

Usage Conditions :

Substrate	Piezoelectric ceramics, transducer types
Printing	200-300 mesh screen printing
Leveling	Let it level at room temperature for 5-15 minutes (adjust time based on actual leveling conditions).
Drying	Bake in a ventilation oven at 100-150°C for 10-15 minutes (if the baking temperature is below 300°C, the baking time may be adjusted according to actual conditions).
Firing Condition	The sintering temperature is 850°C (recommended value) and the sintering time is 9-11 minutes. The sintering range can be adjusted within 800-850°C as needed, but the peak temperature must be maintained for 10 minutes.
Thinner	ST-1000

Characteristics :

1. Paste Characteristics :

Characteristic	Standard	Test Method And Conditions
1 Fineness	$\leq 5\mu\text{m}$	FOG test
2 Viscosity	120-280Pa.s	Brookfield HBT (Boli Fei) viscometer, rotor SC4-14/6R, operating at 10 rpm, with viscosity adjustable to $25\pm 1^\circ\text{C}$ according to user requirements.

2. Characteristics After Curing :

Under the 1-sintering condition, the film thickness is 8-12 μm .

Check fired film produced under the conditions specified in 1) , (Film thickness is 8-12 μm .)



Characteristics		Standard	Test Method And Conditions
3	Resistivity	$\leq 5\text{m}\Omega/\square$	Test pattern 0.6mm×60mm
4	Adhesion Strength		Peel Test: 0.5mmφ Tin plated Cu wire soldered on 2mm×2mm Pad. Solder: 96.5Sn/0.5Cu Mildly activated flux used.
	Initial Adhesion	$\geq 48.5\text{N}$	
	Ageing Adhesion	$\geq 28.6\text{N}$	Aging conditions: 150°C, 24 hours

Save Conditions And Validity Period :

The product shall be stored in a sealed container at an ambient temperature of 5-25°C, with a shelf life of 1 year from the date of shipment.

Packaging Method :

Standard packaging, 1000g/can; samples are available in 200g small can packaging.