



Product Specification

Product:	Conductive Silver Paste
Part Number:	01M-5805

Application Scope :

This product is suitable for quartz glass electrodes.

Usage Conditions :

Substrate	Quartz glass
Printing	200-300 mesh screen printing
Leveling	Let it level at room temperature for 5-15 minutes (adjust time based on actual leveling conditions).
Drying	Bake in a ventilation oven at 100-150°C for 10-15 minutes (if the baking temperature is below 300°C, the baking time may be adjusted according to actual conditions).
Firing Condition	Sintering in a tunnel furnace with air atmosphere, peak temperature 500-600°C (recommended value), 9-11 minutes.
Thinner	ST-1000

Characteristics :

1. Paste Characteristics :

Characteristic		Standard	Test Method And Conditions
1	Fineness	$\leq 5\mu\text{m}$	FOG test
2	Viscosity	80-280Pa.s	Brookfield HBT (Boli Fei) viscometer, rotor SC4-14/6R, operating at 10rpm and $25\pm 1^\circ\text{C}$, with adjustable viscosity according to user requirements.

2. Characteristics After Curing :

Under the 1-sintering condition, the film thickness is 8-12 μm .

Check fired film produced under the conditions specified in 1) , (Film thickness is 8-12 μm .)



Characteristics		Standard	Test Method And Conditions
3	Resistivity	$\leq 5\text{m}\Omega/\square$	Test pattern 0.6mm×60mm
4	Adhesion Strength		Peel Test: 0.5mm φ Tin plated Cu wire soldered on 2mm×2mm Pad. Solder: 96.5Sn/0.5Cu Mildly activated flux used.
	Initial Adhesion	$\geq 41.3\text{N}$	
	Ageing Adhesion	$\geq 21.6\text{N}$	Aging conditions: 150°C, 24 hours

Save Conditions And Validity Period :

The product shall be stored in a sealed container at an ambient temperature of 5-25°C, with a shelf life of 1 year from the date of shipment.

Packaging Method :

Standard packaging, 1000g/can; samples are available in 200g small can packaging.