



## Product Specification

Product:	<b>Conductive Platinum Paste</b>
Part Number:	<b>55H-1805</b>

### Application Scope :

This product is suitable for electrodes in sensor products, specifically platinum electrodes.

### Usage Conditions :

Substrate	Alumina ceramic
Printing	200-300 mesh screen printing
Leveling	Let it level at room temperature for 5-15 minutes (adjust time based on actual leveling conditions).
Drying	Bake in a ventilation oven at 100-150°C for 10-15 minutes (if the baking temperature is below 300°C, the baking time may be adjusted according to actual conditions).
Firing Condition	The sintering temperature is 850~1000°C (recommended value) and the time is not less than 10 minutes. The lowest firing temperature can be as low as 800°C.
Thinner	ST 1000

### Characteristics :

#### 1. Paste Characteristics :

Characteristic	Standard	Test Method And Conditions
1 Fineness	$\leq 5\mu\text{m}$	FOG test
2 Viscosity	120-280Pa.s	Brookfield HBT (Boli Fei) viscometer, rotor SC4-14/6R, 10 rpm, with adjustable viscosity at $25\pm 1^\circ\text{C}$ according to user requirements.

#### 2. Characteristics After Curing :

Under the 1-sintering condition, the film thickness is 8-12  $\mu\text{m}$ .

Check fired film produced under the conditions specified in 1) , (Film thickness is 8-12 $\mu\text{m}$ .)



Characteristics		Standard	Test Method And Conditions
3	Resistivity	$\leq 50\text{m}\Omega/\square$	Test pattern 0.6mm×60mm
4	Adhesion Strength		Peel Test: 0.5mm $\varphi$ Tin plated Cu wire soldered on 2mm×2mm Pad. Solder: 96.5Sn/0.5Cu Mildly activated flux used.
	Initial Adhesion	$\geq 45.2\text{N}$	
	Ageing Adhesion	$\geq 24.6\text{N}$	Aging conditions: 150°C, 24 hours

**Save Conditions And Validity Period :**

The product shall be stored in a sealed container at an ambient temperature of 5-25°C, with a shelf life of 1 year from the date of shipment.

**Packaging Method :**

Standard packaging, 1000g/can; samples are available in 200g small can packaging.